

# Certificate of Test

Quote No.: NC7459

REPORT No.: FNC11685

## COMBUSTIBILITY TEST FOR MATERIALS IN ACCORDANCE WITH AS 1530.1-1994

**TRADE NAME:** Alcadex A1-4mm Fireproof Aluminium Composite Panel with PVDF Coating

**SPONSOR:** CSP-Architectural  
1029-1035 Ballarat Rd  
Deer Park, VIC  
AUSTRALIA

SGI-Architectural  
Unit 31/ 5-7 Inglewood Place  
Baulkham Hills, NSW  
AUSTRALIA

**DESCRIPTION OF TEST SAMPLE:**

The sponsor described the tested specimen as a core material made of inorganic compounds comprising of calcium carbonate ( $\text{CaCO}_3$ ), magnesium hydroxide ( $\text{Mg}(\text{OH})_2$ ) and aluminium hydroxide ( $(\text{Al}(\text{OH})_3$ ), and 0.5% organic compounds.

Nominal thickness: 3 mm (50-mm for the test)  
Nominal density: 955  $\text{kg/m}^3$   
Colour: off white

**TEST PROCEDURE:** Five (5) samples were tested in accordance with Australian Standard 1530 Methods for fire tests on building materials, components and structures, Part 1- 1994: Combustibility Test for Materials.

An alternative suitable insulating material was used to fill the annular space between the furnace tubes, as specified in Clause 4.2 of ISO 1182:2010.

**RESULTS:**


Mean furnace thermocouple temperature rise..... 2.8°C  
Mean specimen centre thermocouple temperature rise .....2.4°C  
Mean specimen surface thermocouple temperature rise..... 1.8°C  
Mean duration of sustained flaming.....0 seconds  
Mean mass loss..... 41.8 %

**DESIGNATION:** The material is NOT deemed COMBUSTIBLE according to the test criteria specified in Clause 3.4 of AS 1530.1-1994.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

DATE OF TEST: 16 December 2015 TEST No.: 11569  
Issued on the 11<sup>th</sup> day of April 2016 without alterations or additions.

  
Heherson Alarde  
Testing Officer

  
Brett Roddy  
Team Leader, Fire Testing and Assessments

Copyright CSIRO 2016 ©. Copying or alteration of this report without written authorisation from CSIRO is forbidden.



NATA Accredited Laboratory  
Number: 165  
Corporate Site No 3625  
Accredited for compliance with ISO/IEC 17025.

CSIRO INFRASTRUCTURE TECHNOLOGIES

14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA  
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555 www.csiro.au

